



BSI Standards Publication

Resilient and laminate floor coverings — Determination of indentation and residual indentation

Part 3: Indentation of resilient semi-flexible/vinyl composition tiles

National foreword

This British Standard is the UK implementation of [ISO 24343-3:2018](#).

The UK participation in its preparation was entrusted to Technical Committee PRI/60, Resilient and Laminate Floor Coverings.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2018
Published by BSI Standards Limited 2018

ISBN 978 0 580 52257 4

ICS 97.150

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 October 2018.

Amendments/corrigenda issued since publication

Date	Text affected
<hr/>	

INTERNATIONAL STANDARD

ISO
24343-3

Second edition
2018-10-31

Resilient and laminate floor coverings — Determination of indentation and residual indentation —

Part 3: Indentation of resilient semi-flexible/ vinyl composition tiles

*Revêtements de sol résilients et stratifiés — Détermination du
poinçonnement et du poinçonnement rémanent —*

*Partie 3: Poinçonnement de carreaux semi-flexibles/carreaux de
composition vinylique résilients*



Reference number
ISO 24343-3:2018(E)

© ISO 2018



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Apparatus	1
6	Atmosphere for conditioning and testing	2
7	Sampling and selection of specimens	3
8	Test procedure	3
9	Calculation and expression of results	3
10	Test report	3
Bibliography		4

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 219, *Floor coverings*.

This second edition cancels and replaces the first edition (ISO 24343-3:2011), which has been technically revised.

The main changes compared to the previous edition are as follows:

- [Clause 2](#) has been added;
- former Clause 9 ("Precision statement") has been removed;
- some minor technical and editorial changes have been made for clarity.

A list of all parts in the ISO 24343 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Resilient and laminate floor coverings — Determination of indentation and residual indentation —

Part 3: Indentation of resilient semi-flexible/vinyl composition tiles

1 Scope

This document describes a method for determining the short-term indentation resistance of resilient semi-flexible/vinyl composition tile (VCT) floor covering after the application of constant load.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 indentation

difference between the initial thickness and the thickness measured after removal of the load

3.2 thickness

distance between two parallel plates where the floor covering is inserted under a specific load

4 Principle

Test pieces are subjected to static loading at room temperature, the thickness being measured before and during loading at specified dwell periods.

5 Apparatus

5.1 Water bath capable of maintaining a temperature of $(23 \pm 2,0) ^\circ\text{C}$.

NOTE This is optional.


5.2 Indenter, consisting of a straight, steel cylinder with the following characteristics:

- diameter of the indenter: $(6,35 \pm 0,01) \text{ mm}$;
- hemispherical foot;

— weight of the indenter: $(0,90 \pm 0,05)$ kg.

5.3 Rigid, horizontal platform of minimum diameter 35 mm.

5.4 Device by means of which a mass of $13,60 \pm 0,12$ kg can be smoothly applied. The frame shall not deform by more than 0,05 mm measured in the direction of the axis under the maximum mass. An example of a device to apply force on an indenter is given in [Figure 1](#).



Key

- | | |
|-----------------------------|---------------|
| 1 rigid horizontal platform | 5 comparator |
| 2 test piece | 6 dead weight |
| 3 annular weight | 7 indenter |
| 4 lever arm | |

Figure 1 — Example of a device to apply force on an indenter

5.5 Comparator for measuring the depth of indentation to $\pm 0,01$ mm.

5.6 Apparatus for measuring the thickness of the test piece to 0,01 mm, with the following characteristics:

- diameter of the foot: $(3,50 \pm 0,02)$ mm;
- mass applied: $(0,085 \pm 0,003)$ kg.

5.7 Stopwatch or other timing device with an accuracy of $\pm 0,2$ s.

6 Atmosphere for conditioning and testing

Unless otherwise stated in the product specification, condition the test pieces at a temperature of (23 ± 2) °C and a relative humidity of (50 ± 5) % for a minimum of 1 h. Maintain these conditions when carrying out the test. Test pieces may also be conditioned by means of a water bath ([5.1](#)) for a minimum of 1 h.

7 Sampling and selection of specimens

Take a representative sample from the available material. Take three test pieces with dimensions at least 50 mm by 50 mm cut from different tiles or planks.

8 Test procedure

8.1 Condition the test pieces as specified in [Clause 6](#).

8.2 Mark the place of measurement and measure the initial thickness of the test piece, t_0 , at its centre to 0,01 mm, using the appropriate mass specified in [5.6](#).

8.3 Place the test piece on the platform.

8.4 Place the indenter on the marked spot and adjust the comparator to zero. Gently apply the mass specified in [5.4](#) and start the stopwatch within 2 s.

8.5 Record the depth of indentation, t_1 , after (60 ± 1) s to 0,01 mm while continuing to maintain the force on the test piece.

8.6 Wait another (540 ± 2) s, resulting in a total indentation time of (600 ± 3) s, and record the depth of indentation, t_2 , of the test piece.

8.7 Repeat the test on the remaining test pieces. Calculate the mean value from the measurements taken and express the result to 0,01 mm.

9 Calculation and expression of results

- a) Calculate the indentation at (60 ± 1) , $I_{60} = t_0 - t_1$, for each test piece.
- b) Calculate the indentation at (600 ± 3) s, $I_{600} = t_0 - t_2$, for each test piece.
- c) Calculate the mean values for both I_{60} and I_{600} for all test pieces, I_{60} (mean) and I_{600} (mean), to the nearest 0,01 mm.

10 Test report

The test report shall contain the following information:

- a) a statement that the tests were performed in accordance with this document, i.e. [ISO 24343-3:2018](#);
- b) complete identification of the product tested, including type, source, colour and manufacturer's reference numbers;
- c) history of the sample;
- d) the individual and mean values for the indentation at 60 s, I_{60} and I_{60} (mean), respectively, to the nearest 0,01 mm;
- e) the individual and mean values for the indentation at 600 s, I_{600} and I_{600} (mean), respectively, to the nearest 0,01 mm;
- f) any deviation from this document which could have affected the results.

Bibliography

- [1] ASTM F 1066, *Standard Specification for Vinyl Composition Floor Tile*
- [2] ASTM F 1914, *Standard Test Methods for Short-Term Indentation and Residual Indentation of Resilient Floor Covering*
- [3] JIS A 1454, *Test methods — Resilient floorcoverings*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
 - A British Standard purchased in hard copy format is for personal or internal company use only.
 - It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK